



BONDEX Regatta

Product Code	340000
Product Name	BONDEX Regatta
Recommended for	Wooden boats
Available sizes	0.75 L - 2.50 L

1 Product Description

1.1	Product Type:	Yacht varnish for treatment of wooden boats - out-and inboard - above the waterline, when a glossy, solid and waterproof surface is required.
1.2	Manufacturer:	Dyrup A/S - Gladsaxevej 300 - 2860 Søborg - Denmark - Phone: +45 39 57 93 00 - www.dyrup.com
1.3	Where to use:	Wooden boats above the waterline.
1.4	Special Qualities:	Resistance towards influence from sea water, sun and wind. Resistance towards common cleaning materials.
1.5	Colour Range:	• 900 Clear
1.6	Form Supplied:	Ready to use.

2 Composition

2.1	Binder:	Oil modified alkyd resin.
2.2	Solvents:	White spirit.
2.3	VOC-content:	EU limit value for this product (cat. A/i): 500 g/l (2010). This product contains max. 199 g/l VOC:
2.4	Pigments:	No pigments.

3 Technical Data

3.1	Specific gravity:	App. 0.9 kg/l.
3.2	Viscosity:	H-K (Gardner-holdt).



3 Technical Data

3.3	Flash point:	62°C, Pensky Martens.
3.4	Gloss:	High gloss, more than 90 at a 60° angle.
3.5	Solid content:	App. 53 W/W%.
3.6	Odour:	Strong.
3.7	Coverage	10-14 m ² /l, depending on the type of wood and the state of substrate.
3.8	Drying time:	<i>Touch dry</i> : app. 2 hours. <i>Recoatable</i> : App. 6 hours. <i>Fully cured</i> : App. 48 hours. Measured at 23°C and standard humidity of 60%.
3.9	Weather resistance:	Water repellent. Contains UV-blocker.
3.10	Thinning:	Do not thin.
3.11	Storage:	Store frost free.
3.12	Shelf life:	5 years in unopened container.

4 Surface and preparation

4.1	In general:	Common safety rules for work with paints and varnishes must be observed. Further information is available from our Material Safety Data Sheet.
4.2	Substrate:	The surface must be clean, dry and solid.
4.3	Humidity / Moisture content:	Do not use at temperatures below 5°C and/or above 80% relative humidity, based on a daily average.

5 Treatment

5.1	Application method:	Apply by brush or roller.
5.2	Pre-treatment:	The most durable result is achieved by priming with Bondex Preserve (on outdoor wood only).
5.3	Treatment:	<i>New wood</i> : 2-3 coats of Bondex Regatta



- 5.4 Renovation of previously treated wood: *Previously varnished wood*: slight sanding, wet or dry. Detached spots should be treated with Bondex Preserve (outdoor only). *Worn-down, discoloured wood*: plane, scratch or sand until sound wood.
- 5.5 Cleaning of tools Clean tools immediately with white spirit.

6 Safety precautions

- 6.1 In general Common safety rules for work with paints and varnishes must be observed. Further information is available from our Material Safety Data Sheet.
- 6.2 Safety instructions. **Warning** Flammable liquid and vapour. Keep out of reach of children. If medical advice is needed, have product container or label at hand. Wear protective gloves. Wear eye or face protection. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse skin with water or shower. Store in a well-ventilated place. Keep cool. Dispose of contents and container in accordance with all local, regional, national and international regulations. Contains 2-butanone oxime. May produce an allergic reaction. Repeated exposure may cause skin dryness or cracking.



7 Disposal

- 7.1 Disposal: Do not empty into drains or into the environment. Product waste must not be poured into the sewers, water reserves or soil. Left over product should be handed in at your local waste disposal. Empty can may be recycled (check with your local waste disposal site or your local authorities).

The purpose of this Technical Data Sheet is to provide our clients with information about the properties and characteristics of the product. The information provided is based on tests conducted by us under usage conditions that comply with the prevailing standards. Our recommendations for use are for information only, and in no event shall they take precedence over any specific recommendation taking into account the nature and conditions of a particular site, nor shall they engage PPG's liability. before all applications of the product, clients should check that this document has not been ammended by a more recent version, which takes into account new technical data. This version annuls and replaces all previous versions of Technical Data Sheets relating to this product.